



Technical Data Sheet

REMA TIP TOP COLD VULCANIZING FLUID

TDS #: RTTNA – 001

Rev. # 2

Rev. Date: 10/5/2015

PART NUMBERS:	201, 202, 203, 204, 205	
CONTAINERS/PACKAGING:	201 – 25 gram tube 203 – 8 fl. oz. can 205 – 1 US gallon can	202 – 50 gram tube 204 – 32 fl. oz. can
FIELD OF APPLICATION:	RTT Cold Vulcanizing Fluid is intended for the installation of RTT Tube Repair Units and RTT Tube Valve Repair Units in either a hot or cold vulcanizing procedure.	
PRODUCT ADVANTAGES:	Suitable for chemical (cold) applications Optimum adhesion for tube repairs Long shelf life	
INSTRUCTIONS FOR USE:	Clean the area to be buffed with Rema Pre-Buff Cleaner Use a low-speed buffer (< 5,000 rpm) to buff the area to be repaired After the repair area has been properly buffed, clean the area with a brass brush to remove any buff particles NOTE: Do not use Pre-Buff Cleaner, solvents, or compressed air on the buff texture Apply an even coat of Cold Vulcanizing Fluid to the buffed area Allow to dry (drying time depends on atmospheric conditions) NOTE: Do not use compressed air, heat guns, or other artificial means to aid in the drying process Close container tightly after using	
SAFETY INSTRUCTIONS:	Do not use for the application of any tire repair materials, i.e. Radial or Bias Repairs, Minicombis, Stems, Sealastic, A&B Compound, Camplast, T-2 Compound, Super RAS, Envelope, etc.	
SHELF LIFE:	Four (4) years in unopened container from date of manufacture	
BASE SOLVENT:	Trichloroethylene (refer to SDS for detailed data)	
RECOMMENDED STORAGE CONDITIONS:	Store in a dark, moisture free environment, away from direct sunlight Protect from freezing Comply with all local, state, and federal regulations	



Technical Data Sheet

REMA TIP TOP COLD VULCANIZING FLUID

TDS #: RTTNA – 001

Rev. # 2

Rev. Date: 10/5/2015

DRYING TIME: Minimum of 5 minutes (drying time depends on atmospheric conditions, and may be longer in cold, humid areas)

WAIT TIME for RETURNING TIRE TO SERVICE: No wait time is required when used in conjunction with Rema Tip Top Tube Repairs

ADDITIONAL INFO: Do not dilute. Use full strength only!

CANADIAN REGULATIONS

WHMIS CLASIFICATION: D1A, D2A, D2B

This product is regulated under the Canadian Controlled Products Regulations.

WHMIS INFORMATION:

WHMIS Classification: D1A, D2A, D2B

Component Analysis - WHMIS IDL

The following components are identified under the Canadian Hazardous Products Act Ingredient Disclosure List:

Component	CAS #	Minimum Concentration
Trichloroethylene	79-01-6	1 % (English Item 1612, French Item 1646)

NOTICE: REMA TIP TOP / NORTH AMERICA believes that the information contained on this data sheet is accurate. It is based on extensive tests and represents standard values. However, it may not contain information on all confirmed properties. REMA TIP TOP / North America reserves the right to carry out improvements and technical development to this product at its discretion. For detailed application instructions, always refer to the appropriate Rema Tip Top Instruction Manuals and/or Repair Instruction CD's. The suggested procedures are based on experience as of the date of publication. They are not necessarily all-inclusive, nor fully adequate in every circumstance. Also, the suggestions should not be confused with nor followed in violation of applicable laws, regulations, rules or insurance requirements.

NO WARRANTY IS MADE, EXPRESS OR IMPLIED, OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE OR OTHERWISE.